

DOI: 10.34854/ICPAF.52.2025.1.1.248

**DEVELOPMENT STATUS OF LARGE-SCALE COLLECTING MIRRORS FOR DTS
ITER ^{*)}**

¹Tereshchenko I., ¹Samsonov D., ¹Mukhin E., ¹Marchiy G., ¹Kuznetsov F., ²Marinin G.,
²Terentyev D., ³Piskarev P., ³Makhankov N., ⁴Patrikeev V., ⁵Solk S., ⁶Khudoley A.,
⁶Kumeisha P., ⁷Koroleva A., ¹Tolstyakov S., ⁸Chernakov P., ⁹Mokeyev A.

¹*Ioffe Institute, St.-Petersburg, Russia*

²*RUSSIAN TECHNOLOGIES LLC, St.-Petersburg, Russia*

³*JSC "NII EFA named after. D.V. Efremova", St. Petersburg, Russia*

⁴*Lytkarino Optical Glass Plant, Lytkarino, Russia*

⁵*Research Institute optical-electronic instrumentation, Sosnovy Bor, Russia*

⁶*A.V. Luikov Heat and Mass Transfer Institute, Minsk, Belarus*

⁷*SPbSU Physical Methods of Surface Research, Saint Petersburg, Russia*

⁸*Spectral-Tech, St.-Petersburg, Russia*

⁹*Institution 'Project Center ITER' RF DA, Moscow, Russia*

Collecting systems of ITER optical diagnostics contain a significant number of in-vacuum mirrors, which must have high optical stability under conditions of exposure to neutron fluxes (max.) $2.25 \cdot 10^{12} \text{ cm}^{-2} \text{ s}^{-1}$, thermal cycling 70-180°C, vibration loads, contamination of the reflecting surface with erosion products first wall - W, Be and their compounds, emergency steam breakthrough (SI) 30-250°C at RH more than 90%. DTS system consists of 7 large-scale in-vacuum mirrors with linear dimensions from 360 to 720 mm and made of 316L(N)-IG stainless steel. The optical design of the collection system involves 5 consecutive reflections, therefore the reflectance of each mirror must be above 90% in the range of 500-1100 nm. The quality of scattered radiation transmission is determined by such characteristics of mirrors as stability of shape and spatial position and spectral characteristics of diffuse and specular reflections. The choice of stainless steel 316L(N)-IG as the mirror material and the developed mounting design made it possible to reduce unwanted deformations of the mirror optical surface under applied loads. Since the reflection of stainless steel is ~60-70%, it is necessary to deposit a highly reflective optical coating. Silver is highly reflective in the visible and NIR regions but is susceptible to corrosion when exposed to H⁺ and OH⁻ ions present in water vapor. The barrier type of protection for the reflective Ag layer was chosen - deposition of a thin multilayer dielectric coating with a total thickness ~ 30 nm. The experiments showed that with the same total thickness of the protective coating, increasing the number of interfaces in the protective coating reduces the drop in reflection after SI, and with 5 layers it is practically absent.

Diffuse reflectivity characteristics of mirrors are affected by the degree of surface preparation before deposition. A comparison was made of small-sized 316L(N)-IG stainless steel samples with abrasive polishing, magnetorheological polishing, diamond turning, and glass-coated stainless-steel surfaces.

The report was created as a report on work for the ITER Organization (Rosatom contract No. H.4a.241.19.22) and supported by the Ioffe Institute (RF state assignment 0034–2019–0001). Microanalysis of the coated samples was undertaken with the cooperation of St. Petersburg State University (project code AAAA-A19-119091190094-6).

^{*)} [abstracts of this report in Russian](#)